



S20-FA16

Surfacing Veil for Polyester Laminates

PRODUCT DESCRIPTION

The product S20-FA16 consists of glass fibres with a nominal length of 10 mm and a nominal diameter of 10-11 µm. The glass fibre veil is bound by polyvinyl alcohol.

The product is designed as a surfacing veil for polyester laminates.

The low level of binder content improves the impregnation with resins.



TECHNICAL CHARACTERISTIC (nominal values)

PROPERTY	TEST METHOD	UNIT	SPECIFICATION NOMINAL
Area Weight	ISO 536	g/m ²	19
Tensile Strength (md)	ISO 1924/2	N/50 mm	50
Tensile Strength (cd)	ISO 1924/2	N/50 mm	40
Loss on Ignition	ISO 1887	%	12



**OWENS CORNING
COMPOSITE MATERIALS, LLC**
ONE OWENS CORNING PARKWAY
TOLEDO, OHIO 43659
1.800.GET.PINK™
www.owenscorning.com
www.owenscorning.com/composites
Contact:
nonwovensinfo@owenscorning.com

**OWENS CORNING
FIBERGLAS, SPRL.**
166, CHAUSSÉE DE LA HULPE
B-1170 BRUSSELS
BELGIUM
+32.2.674.82.11
Contact:
nonwovensinfo@owenscorning.com

**OWENS CORNING
SHANGHAI COMPOSITES CO. LTD.**
OLIVE L.V.O. MANSION, 2ND FLOOR
620 HUASHAN ROAD
SHANGHAI 200040
CHINA
+86.21.62489922
Contact:
nonwovensinfo@owenscorning.com

This information and data contained herein is offered solely as a guide in the selection of a reinforcement. The information contained in this publication is based on actual laboratory data and field test experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production. It is important for the user to determine the properties of its own commercial compounds when using this or any other reinforcement. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law safety code or insurance regulation.

OCV™ Non-Woven Technologies reserves the right to modify this document without prior notice. ©2008 Owens Corning.